

# Roof Reviver (Pigment Additive)

## Product Information

A highly concentrated inorganic pigment that has been formulated and measured to provide a superior combination with the Roof Reviver Top Coat Base, that will enhance the appearance & protect old weathered cement tile roofs.

### PRODUCT FEATURES

- 100% Inorganic Pigment
- Outstanding UV Stability
- Excellent Opacity Level

Colour	Concentrated Pigment (from colour range)
Appearance when dry	N/A
Storage Temperature	Minimum 10°C, Maximum 50°C
Shelf Life (months)	12
Pack Size	1 L (volume content 1Kg)

### ESTIMATION

Solids Content	47% ± 1
Dry film thickness	N/A
Wet film thickness	N/A
Theoretical Coverage	5 m <sup>2</sup> /L per coat (in combination with Roof Reviver Topcoat)

### APPLICATION

**Add to "Roof Reviver" (Topcoat Base)** - can only be added to Roof Reviver Topcoat Base.  
1 Kg of Roof Reviver Pigment Additive is to be dispensed into a 1 bucket of Roof Reviver Base.

Mixing on site – Add Roof Reviver 1kg Pigment Additive to the Roof Reviver Top Coat Base then mix mechanically with drill on a low speed until product is fully incorporated.  
If mechanical mixer is unavailable stir thoroughly with a broad paddle ensuring pigment product is fully dispersed and incorporated.

### APPLICATION DETAILS

Maximum Relative Humidity	75%
Application Temperature Range	10°C - 35°C
Methods	The same as Roof Reviver Top Coat Base.
Cleaning Solvent	Water (Copious quantities)
Max. Volume Thinners	0% (Should not be thinned)
Nozzle Orifice Airless spray	21-27 Thou
Fan Angle	30° - 60°
Nozzle Pressure	Between 1200-2000 psi (May vary due to size of airless machine)

Care must be taken not to half dispense pigment as it will effect to opacity level of the final product. Please ensure when dispensing not to spill, as it is a very concentrated pigment additive, that will stain and may be very hard to clean up.

### DRYING CHARACTERISTICS

Temperature (degree C)	10°C	20°C
Touch dry	2 hours	1 hour
Handle dry	4 hours	2 hours
Full cure	16 hours	8 hours

Overcoating – Where possible allow dry time between coats for a minimum of two hours at 20°C & 50% relative humidity. Apply 2<sup>nd</sup> coat of "Roof Reviver" to enhance finished gloss level.